

## Maleki-SBS 860

### Silicate reprofiling and grout mortar

Item-No.: 1520

High performance, environmentally friendly silicate mortar for sewage water areas. Extreme resistance against chemicals in the range of pH 0 – 14.

### Technical data

<b>Mixing ratio</b>	0.75 – 0.85 l water per 5 kg powder	<b>Grain</b>	0 – 2 mm
Slurry	0.85 L		
Creamy	0.75 – 0.8 L		
<b>Compressive strength</b>	≥ 35 N/mm <sup>2</sup>	<b>Flexural strength</b>	approx. 10 N/mm <sup>2</sup>
<b>Processing temperature</b>	min. +10 °C max. +35 °C	<b>Processing time at 20°C</b>	approx. 35 min
<b>Relative humidity</b>	Max. 80%		
<b>Application thickness</b>	4 – 50 mm	<b>Consumption</b>	approx. 0.2 – 2 kg/m <sup>2</sup> * approx. 8 kg /m <sup>2</sup> at a layer thickness of 4 mm
<b>Joint gap</b>	5 – 20 mm		
<b>Loadability**</b>	Curing at 20°C	<b>Density</b>	approx. 1.3 kg/dm <sup>3</sup> approx. 2.0 kg/dm <sup>3</sup>
Walkable	1 day		
Full water load	2 days		
Fully loadable	3 days		
Chemical load	7 days		

\* Depending on joint gap

\*\* In closed vessels, sufficient ventilation and drying must be ensured. A suitable heater fan must be used for this purpose.

### Properties

- Silicate-Technology
- environmentally friendly
- mineral
- VOC – and APEO-free
- high chemical resistance at the range of pH 0 – 14
- sulfate resistant according to DIN 4030
- salt water resistant
- waterproof up to 1.5 bar
- extrem high adhesion on substrate
- high surface hardness and abrasion resistance
- easy application

### Range of usage

- for indoor and outdoor use
- for reprofiling and joint work in mechanical and chemical stressed areas:
- for general canal or sewage construction
- acid resistant installations
- agriculture
- garages and warehouses
- laboratories
- commercial kitchens
- breweries

### Product systems

- Sewer renovation
- Acid protection

### Preparation of substrate

Prior to coating or jointing, ensure that the surface is stable and has sufficient surface tensile strength. The surface should also be ready for coating, dry or matt damp, clean and free from all kinds of debris. Ensure a sufficient joint depth of at least 5 mm. The edges must be free from oil and grease. For reprofiling applications mechanical surface preparation e.g. shot-blasting is recommended. Due to roughening the surface, the adhesion for the subsequent layer can be improved.

Deeper ruptures must be filled with Maleki-RM 500 or Maleki-VM 530. The surface should be permanently vibration-free and crack-free. Already existing cracks must be repaired professionally. The adhesive strength of the substrate must be at least 1.5 N/mm<sup>2</sup>.

Application of waterproofings for areas with water under pressure is only possible on concrete surfaces.

Pre-wet absorbent surfaces until the surface is matt damp. Avoid puddles. In case of pressing water or acute leakages the substrate must be pre-filled before application of Maleki-SBS 860. Therefore, the specific spots are treated or filled with water stop cement to ensure sufficient curing of the subsequent waterproofing. In case of internal waterproofings against negative water pressure, the substrate must provide a sufficient bonding strength.

## Rounding of edge areas

For rounding of wall-floor or wall-wall transitions use Maleki-DS 220 or Maleki-DS 240 for preparation of coves. Please refer to the respective technical data sheets for more information. All cove areas must be fully covered with Maleki-SBS 860 for a complete waterproofing and protection against damaging chemicals.

## Mixing and application

Mix the material by using a mixing machine. First, add 0.75 – 0.85 liters of water per 5 kg powder material into the mixing container. Then, pour the powder inside while stirring. For manual applications the hand-held mixer BSM 2882 by Baier Tools and the Collomix mixing paddle KR 140 HF are recommended. By using the respective mixing paddle, a proper thread adapter must be used. For mixing of partial quantities in smaller containers the mixing paddle KR 90 S for drilling machines is recommended. The material has to be mixed intensely for 1 minute.

In the beginning the mortar looks dry to semi-dry. After a setting time of 3 minutes the material is mixed again for 1 more minute. Mix only as much material as can be applied within 35 minutes. Maleki-SB 860 must not be mixed with cement-based products. Do not mix Maleki-SWP 270 with any other liquid component except water.

## Grout mortar

For the use as acid resistant grout mortar for ceramic tiles Maleki-SBS 860 is filled into the open joint network with a flexible jointing board by using the usual technique. After complete filling remove excess material from the surface diagonally to the joint direction. For grouting of rougher surfaces (canal clinkers and canal sole half shells, etc.) Maleki-SBS 860 is applied with standard jointing board and suitable joint trowel.

To clean the grouting use a washboy-set. This must either be new or must have been used solely for silicate-based products. Dampen the surface with the sponge board slightly (max. matt damp) and clean the tile surface after 1 minute of contact time. Use minimum amount of water! Avoid water puddles on tiles and joints.

Replace the cleaning water as often as no residues remain on the surface. Any initially dried residue still left is removed by cleaning the entire surface with clean water. Any initially dried residue still left is removed by cleaning the entire surface with clean water. All residues which run down the wall surface should be removed with a sponge. Due to the minimum amount of water during the cleaning procedure a clean and edge-free joint pattern may not be achieved.

## Reprofiling work:

For optimal adhesion and for complete filling of the substrate to be coated Maleki-SBS 860 is applied by fulling with a brush. Therefore, the material is mixed as a slurry.

The second coating is applied wet-in-wet by trowel up to the intended layer thickness. Please refer to the table above for the required mixing ratio for each procedure.

If the application of the respective layers is not possible directly one after the other, the first or previous layer must be fully cured before application of the second or third coat. Depending on the ambient conditions, this can be guaranteed after 24

hours at the earliest. The subsequent layer is applied without pre-wetting.

Open Maleki-SBS 860 bags must be sealed airtight or have to be processed within 6 hours. For further applications in lower layer thicknesses, we recommend the use of Maleki-SWP 270.

Therefore, the application of Maleki-SWP 270 should also be done wet-in-wet. If this is not possible, follow the procedure described above.

## Post-processing and coating protection

If smoothing of the surface is necessary after the end of the processing time, this step should be carried out without additional water.

The coating has to be protected from too quick drying (solar radiation, draft), frost and rain for 2 days. Therefore, a complete enclosure of the building site may be necessary. Do not cover the finished surface with foils or other materials. To avoid dew formation on the mortar surface, the ambient temperature must be 3°C above the respective dew point. If Maleki-SBS 860 is applied in closed rooms, vessels or shafts, an additional ventilation or drying system is essential. Otherwise, there would be a danger of moisture condensation.

For early loading (water and acid load) of new surfaces apply a protective layer of Maleki-VS 930 after one day. The ready-to-use mixture is applied in two steps. The consumption is approx. 50 g/m<sup>2</sup>. The treated surfaces are loadable after one day. For further information about the application of Maleki-VS 930 please refer to the corresponding technical data sheet.

## Tools and cleaning

Mixing device, stirrer, brush, trowel, jointing board joint trowel, washboy set.

All equipment should be washed clean and dried before and after application.

## Packaging and shelf-life

3 x 5 kg bags of mortar in a bucket.

100 x 5 kg bags of mortar in a carton.

Original packing is storable for 9 months in dry and controlled temperate areas (not below 0 °C, recommended 10 – 25 °C). Reseal opened containers immediately and use within a very short time.

## Associated products

Maleki-RM 500	Item-No. 1416
Maleki-VM 530	Item-No. 1442
Maleki-DS 220	Item-No. 1314
Maleki-DS 240	Item-No. 1329
Maleki-SWP 270	Item-No. 1312
Maleki-SBS 860	Item-No. 1520
Maleki-VS 930	Item-No. 1828

## Safety notes

Maleki-SBS 860 reacts alkaline with moisture/water. Avoid inhaling dust when opening packaging. Protect skin and eyes during the mixing process.

# Technical data sheet


TM SBS 860\_en - Version 2.7  
Stand: 17.11.2023

Please refer to the Material Safety Data Sheet which can be requested on [www.malekigmbh.com](http://www.malekigmbh.com) for further information on safety during transportation, storage, handling and disposal. Follow instructions on the packaging.

## Notes

Because of different properties of the substrates and the environment we cannot guarantee a uniform coloring. The appearance should be tested on a separate location if required. Therefore, this product is not suitable for decorative purposes. Mix Maleki-SBS 860 only with the specified amount of water. Do not use on substrates with different surface temperatures (for example hot water and heating pipes or direct sunlight). Do not apply Maleki-SBS 860 on frozen substrates or in freezing conditions and do not apply during rain. Use structural measures such as expansion joints to prevent formation of cracks in buildings. An appropriate flexible or permanently elastic sealant must be used to waterproof joints. The absorbency of the substrate and the tile edges must be uniform. The tile surface must be free of all cement and gypsum residues. Do not mix with cement-based products. Maleki-SBS 860 is a special-purpose product which requires previous work instructions before first use. The use of Maleki-SBS 860 is permitted up to an acid concentration of 5%.

The content of this technical data sheet corresponds to the latest development and our applications experience. All information is based on ideal conditions and therefore does not apply for every application purpose. Due to different materials, substrates and different actual site conditions no warranty is given for the customer's application. In particular, we assume no liability based on this information or any verbal statements. The only exception is when we can be blamed for the case of intent or gross negligence. In that case the customer has to prove that he has transmitted all required information completely and in a timely manner for a proper and promising evaluation by Maleki GmbH. Any further details regarding the application of our products have to be confirmed in writing by Maleki GmbH. The customer must test the product's suitability for the intended application and purpose. We reserve the right to change the product specifications due to the ongoing development. Apart from that our general terms and conditions are valid. This data sheet supersedes all earlier technical data on this product. The technical data sheet can be requested on [www.malekigmbh.com](http://www.malekigmbh.com).

	
<b>Maleki GmbH</b> Carl-Stolcke-Straße 1 49090 Osnabrück Fon. +49 541 2024799-0 Fax. +49 541 2024799-9  16 No. 1520 EN	
<b>EN 1504-3:2005</b> Concrete protection and repair product for statically non-relevant restoration. <b>EN 1504-3: ZA.1a</b>	
Compressive strength	Class R2
Chloride ion content	≤ 0,05 %
Adhesion	≥ 0,8 MPa
Impaired expansion	≥ 0,8 MPa
Carbonization resistance	NPD
Elastic modulus	NPD
Fire behavior	A1